

# *Dow Corning*<sup>®</sup> SE 9189 L Gray or White RTV Adhesive

## **FEATURES**

- Fast tack free RT cure
- Flowable
- Cures to soft, low stress elastomer
- Pigmented to hinder component identification
- UL 94 V-0 flammability rating
- Controlled silicone volatility
- No added solvents

## **BENEFITS**

- RT cure, no ovens required
- Mild heat acceleration can speed in-line processing
- Soft coating can improve reliability against stress
- Can be considered for uses requiring flame resistance

## **COMPOSITION**

- 1-part, gray or white
- Polydimethylsiloxane

## **APPLICATION METHODS**

- Automated or manual needle
- Flow

1-part, white or gray, fast tack free flowable viscosity conformal coating with controlled volatility and good flame resistance

## **APPLICATIONS**

- PDP module assembly
- Parts fixing on circuit board

## **TYPICAL PROPERTIES**

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

<b>Property</b>	<b>Unit</b>	<b>Value</b>
Viscosity	cP	23300
	mPa-sec	23300
	Pa-sec	23.3
Fluidity	in	2.7
	mm	68.5
Specific Gravity (Cured)	-	1.18
NVC (Non Volatile Content)	%	97.6
Tack-Free Time at 25°C	minutes	8
Tensile Strength	psi	320
	MPa	2.2
	kg/cm <sup>2</sup>	22
Elongation	%	235
Durometer Shore A (JIS)	-	33
Unprimed Adhesion - Lap Shear (Glass)	psi	190
	MPa	1.3
	N/cm <sup>2</sup>	131
Dielectric Strength (JIS K 6249)	Volts/mil	625
	kV/mm	25
Volume Resistivity (JIS K 6249)	ohm*cm	9.0 E+14
Dielectric Constant @ 1MHz (JIS K 6249)	-	3.1
Dissipation Factor @ 1MHz (JIS K 6249)	-	0.0004
UL Flammability Classification	NA	94 V-0

## DESCRIPTION

*Dow Corning*<sup>®</sup> SE 9189 L Gray or White RTV one-part moisture cure adhesives are generally cured at room temperature and in an environment of 30 to 80 percent relative humidity eliminating the need for curing ovens and the associated costs of energy and capital. Greater than 90 percent of full physical properties should be attained within 24 to 72 hours and varies according to product. Faster manufacturing throughput can be achieved since the adhesive and component can be handled in much shorter times of about 10 to 120 minutes, depending on the adhesive selected and the amount applied. These adhesives are not typically used in highly confined spaces or where a deep section cure is required as they generally cure from the exposed surface inward at a rate of 0.25 inch per seven days. Cure progresses from the outer exposed surface and is dependent on the moisture in the air. Working time is generally a few minutes to an hour for these products until a surface skin begins to form. Mild heat below 60°C (140°F) may be used to increase through-put by accelerating the cure. *Dow Corning* silicone adhesives retain their original physical and electrical properties over a broad range of operating conditions which enhance the reliability of and service life of electronic devices. The stable chemistry and versatile processing options of these adhesives offer benefits for a variety of electronics needs from increasing component safety and reliability, reducing total cost or increasing the performance envelope of devices or modules. Underwriters Laboratory (UL) 94 recognition is based on minimum thickness requirements. Please consult the UL Online Certifications Directory for the most accurate certification information.

## PACKAGING

RTV Adhesives are typically packaged in 100 ml syringes and 330 ml cartridges, 1 kg tubs and pails (18 - 25 kg). In general, *Dow Corning* adhesives/sealants are supplied in

nominal 0.45-, 3.6-, 18- and 200-kg (1-, 8-, 40- and 440-lb) containers, net weight. Not all products may be available in all packages and some additional packages, such as a bladder packs or tubes, may be available for certain package sizes.

## USABLE LIFE AND STORAGE

For best results, *Dow Corning* RTV adhesives should be stored at or below the storage temperature listed on the product label. Special precautions must be taken to prevent moisture from contacting these materials. Containers should be kept tightly closed with head or air space minimized. Partially filled containers should be purged with dry air or other gases, such as nitrogen. Shelf life is indicated by the "Use Before" date found on the product label.

## PREPARING SURFACES

All surfaces should be thoroughly cleaned and/or degreased with *Dow Corning*<sup>®</sup> brand OS Fluids, naphtha, mineral spirits, methyl ethyl ketone (MEK) or other suitable solvent. Solvents such as acetone or isopropyl alcohol (IPA) do not tend to remove oils well, and any oils remaining on the surface may interfere with adhesion. Light surface abrasion is recommended whenever possible, because it promotes good cleaning and increases the surface area for bonding. A final surface wipe with acetone or IPA is also useful. Some cleaning techniques may provide better results than others; users should determine the best techniques for their particular applications.

## SUBSTRATE TESTING

Due to the wide variety of substrate types and differences in substrate surface conditions, general statements on adhesion and bond strength are impossible. To ensure maximum bond strength on a particular substrate, 100 percent cohesive failure of the adhesive in a lap shear or similar adhesive strength test is desired. This ensures compatibility of

the adhesive with the substrate being considered. Also, this test can be used to determine minimum cure time or can detect the presence of surface contaminants such as mold release agents, oils, greases and oxide films.

## ADHESION

*Dow Corning* silicone adhesives are specially formulated to provide unprimed adhesion to many reactive metals, ceramics and glass, as well as to selected laminates, resins and plastics. However, good adhesion cannot be expected on non-reactive metal substrates or non-reactive plastic surfaces such as fluorinated materials, polyethylene or polypropylene. Special surface treatments such as chemical etching or plasma treatment can sometimes provide a reactive surface and promote adhesion to these types of substrates. *Dow Corning*<sup>®</sup> brand Primers can be used to increase the chemical activity on difficult substrates. Poor adhesion may be experienced on plastic or rubber substrates that are highly plasticized, because the mobile plasticizers act as release agents. Small-scale laboratory evaluation of all substrates is recommended before production trials are made.

## USEFUL TEMPERATURE RANGES

For most uses, silicone elastomers should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low- and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the

durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

## **SOLVENT EXPOSURE**

When liquid or vapor solvent or fuel exposure can occur in an application, the silicone adhesive discussed in this brochure is intended only to survive splash or intermittent exposures. It is not suited for continuous solvent or fuel exposure. Testing should be done to confirm performance of the adhesives under these conditions.

## **HANDLING**

### **PRECAUTIONS**

#### **PRODUCT SAFETY**

#### **INFORMATION REQUIRED**

#### **FOR SAFE USE IS NOT**

#### **INCLUDED IN THIS**

#### **DOCUMENT. BEFORE**

#### **HANDLING, READ PRODUCT**

#### **AND MATERIAL SAFETY DATA**

#### **SHEETS AND CONTAINER**

#### **LABELS FOR SAFE USE,**

#### **PHYSICAL AND HEALTH**

#### **HAZARD INFORMATION. THE**

#### **MATERIAL SAFETY DATA**

#### **SHEET IS AVAILABLE ON THE**

#### **DOW CORNING WEB SITE AT**

#### **DOWCORNING.COM, OR**

#### **FROM YOUR DOW CORNING**

#### **REPRESENTATIVE, OR**

#### **DISTRIBUTOR, OR BY**

#### **CALLING YOUR GLOBAL**

#### **DOW CORNING CONNECTION.**

## **HEALTH AND**

## **ENVIRONMENTAL**

## **INFORMATION**

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our web site, [dowcorning.com](http://dowcorning.com) or consult your local Dow Corning representative.

## **LIMITATIONS**

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## **LIMITED WARRANTY INFORMATION PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

## **DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

## **DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

*We help you invent the future.™*

**[dowcorning.com](http://dowcorning.com)**