

DOW CORNING**Electronics Fast Formulation****Dow Corning® 3-1944HP – Data Sheet**

This product is a **Fast Formulation** version of 3-1944. While not all properties have been fully tested, the following reflects the best information we have to date for this product.

Property	Value
As Supplied	
Viscosity at 5 rpm	12,000 cp
Viscosity at 0.5rpm	53,000 cp
Thixo Ratio	4.4
Skin Over Time	8 min
As Cured	
Color	Translucent
Specific Gravity	1.0
Hardness, Shore A	32
Tensile Strength	200 psi
Elongation at Break	180 %

For information on mixing, working time, cure time, temperature ranges, repairability, compatibility, storage, limitations, packaging, safe handling information, health & environmental, and the limited warranty, please reference the Dow Corning product information sheet for dielectric gels. This document can be downloaded from the Dow Corning website at www.dowcorning.com.

Dow Corning believes it is an accurate representation of the typical characteristics and/or potential uses of the product or products as characterized to date. However, the properties of this material and its components have not been completely studied. It is your responsibility to thoroughly test the product in your specific application to determine its performance, efficacy and safety. Therefore, we recommend that use and disposal of this material should be supervised by technically qualified individuals. Suggestions of uses should not be taken as inducements to infringe any particular patent.

Specification Writers: Please obtain copies of the Dow Corning Sales Specifications for these products and use them as a basis for your specifications. They may be obtained from any Dow Corning Sales Office, or from Dow Corning Customer Service in Midland, MI. when the product becomes available for sale.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY:

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Dow Corning specifically disclaims any other express or implied

DOW CORNING

Electronics Fast Formulation

warranty of fitness for a particular purpose or merchantability. Dow Corning disclaims liability for any incidental or consequential damages.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.